

STEP-KO PRODUCTS

MATERIAL SPECIFICATIONS

	DIELECTRIC STRENGTH VOLTS/MIL	RECOMMENDED MAX. TEMP. for CONTINUOUS USE	Water ABSORPTION
GASKETS: Neoprene Faced Phenolic	500	175 degree	.45%
Plain Phenolic	500	225 degree	1.1%
Warrior (Phenolic)	600	266 degree	1.5%
Warrior (G-10)	800	284 degree	.10%
Assureaseal SSC	800	350 degree	.05%
Assureaseal HT	760	356 degree	.2%
SLEEVES: Polyethylene	400-500	180 degree	.01%
Phenolic	500	250 degree	2.0%
Mylar	400	350 degree	.22%
Nomex	690	428 degree	*
G-10	550	285 degree	.10%
Integral	450	300 degree	.9%
WASHER: Phenolic	400	225 degree	1.1%
G-10	550	285 degree	.10%
SEALS: Nitrile			
Viton			
Teflon			

ORDER SPECIFICATIONS

The following data is presented to simplify your ordering procedures and help you eliminate errors in the ordering process.

